# Technical Datasheet



# **ISOMAT STANDARD COLOR**

# **Emulsion paint for interior use**

#### **Description**

ISOMAT STANDARD COLOR is a matt emulsion paint for use on interior walls and ceilings. Suitable for new or old surfaces requiring periodic repainting, e.g. public buildings, hotels, hospitals, schools, etc. Features very good opacity and surface coverage while offering great workability and flow. Has quick-drying and recoat times. Nearly odorless. Delivers a beautiful matt finish.

# Fields of application

ISOMAT STANDARD COLOR is suitable for use on new and old interior surfaces, on all common building materials such as concrete, plaster, gypsum board, etc.

#### **Technical data**

Colors: white and

selected colors through

ISOMAT COLOR

SYSTEM

Type: emulsion paint

Volume solids:  $41 \pm 2\%$ Dry film thickness:  $32 \pm 3 \mu m$ 

Dry film thickness: (EN ISO 2808)

Dry film thickness:  $74 \pm 5 \mu m$ 

(EN ISO 2808)

Viscosity: 115 ± 5 KU

(ASTM D562)

Density:  $1.61 \pm 0.03 \text{ kg/l}$ 

(EN ISO 2811-1)

Adhesion:  $\geq 1.25 \text{ N/mm}^2$ 

(EN ISO 4624)

pH: 8-9.5

(EN ISO 4316)

Drying time: 1 h (touch dry)

(EN ISO 9117)

Recoat time: 3-4 h

(EN ISO 9117)

Vapor permeability:  $S_d = 0.01 \pm 0.005 \text{ m}$ 

(EN ISO 7783-2:  $V_1$  high  $S_d < 0.14$ )

Capillary water

absorption:  $w = 1.2 \pm 0.05 \text{ kg/m}^2 \text{h}^{0.5}$ 

(EN ISO 1062-3: W<sub>1</sub> high 0.50<w) VOC content: 14.5 a/l

Measurements acc. to EN 13300

Gloss level: < 10, Matt

(EN ISO 2813: < 10 at 85°)

Whiteness: ≥ 86%

(EN ISO 6504-3)

Wet scrub resistance: CLASS 3 (EN ISO 11998:  $\geq$  20  $\mu$ m and < 70  $\mu$ m,

at 200 wash cycles)

Cleaning of tools:

Tools should be cleaned with water immediately after use.

#### Directions for use

#### 1. Substrate preparation

The substrate should be dry and free of grease, loose particles, dust, etc.

- Cracks or joints may be filled with ISOMASTIC-A acrylic sealant or ISOMAT ACRYL-STUCCO acrylic filler.
- Concrete imperfections should be repaired with DUROCRET polymer-modified mortar.
- Plastered wall may be repaired with UNICRET and UNICRET-FAST premixed mortars.
- For smoothing of surfaces, STUCCOCRET powder filler should be used.

The substrate should be primed with the concentrated, acrylic water-based primer ISOMAT PROFESSIONAL PRIMER, thinned 300-400% with clean water.

Loose or crumbly substrates should be primed with the acrylic, micronized, water-based primer PRIMER-CLASSIC, thinned up to 50% with clean water.

Surfaces stained by smoke, nicotine, exhaust fumes, water-soluble markers, pencils, etc. should be primed with the stain blocker BLOCK-PRIMER. Priming is not necessary on already painted surfaces providing the old paint is sound.





# ISOMAT STANDARD COLOR

#### 2. Application

ISOMAT STANDARD COLOR should be thoroughly stirred before use. It is applied as is or thinned 5-10% with clean water, in two coats, with a roller, brush, or airless spray. The second coat is applied once the first coat has completely dried.

#### Coverage

ISOMAT STANDARD COLOR covers approx. 12 m<sup>2</sup>/l per coat, on previously prepared surfaces.

## **Packaging**

ISOMAT STANDARD COLOR is supplied in containers of 3 I and 9 I.

## Shelf life – Storage

24 months from production date if stored in original, unopened packaging, at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

## **Volatile Organic Compounds (VOCs)**

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory a, type WB, is 30 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOMAT STANDARD COLOR contains a maximum of 30 g/l VOC.

ISOMAT S.A.
BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000

www.isomat.eu e-mail: support@isomat.eu